

## FNT300-2650085B

### Polyimide Coated Bend-insensitive Multimode Fiber

Bend-insensitive graded-index Multimode fiber with the following properties<sup>1</sup>:

#### 1. Geometrical features

Core Profile	Ge-doped fused silica, graded-index
Cladding Ø	125 µm ± 2µm
Core Ø	50 µm ± 2.5 µm
Core/Clad Concentricity Error	≤ 1.5 µm
Cladding Non-circularity	≤ 2.0%
Coating Ø	160 µm ± 10µm
Coating/ Clad Concentricity Error	≤ 5µm
Coating Material	Polyimide

#### 2. Optical properties

Bandwidth (OFL) @ 850nm	>500 MHz.km
Bandwidth (OFL) @ 1300nm	>500 MHz.km
Attenuation @ 850 nm	< 2.6 dB/km
Attenuation @ 1300 nm	< 0.8 dB/km
Numerical Aperture	0.200 ± 0.015
Macrobend Loss @ 850nm	
2 turns, 15 mm radius	≤ 0.1 dB
2 turns, 7.5 mm radius	≤ 0.2 dB

#### 3. Mechanical properties

Proof-test (100 %)	≥ 100 kpsi
Dynamic Tensile Strength Unaged Fiber (0.5m), Median Tensile Strength	≥ 3.8 GPa
Dynamic Fatigue Stress Corrosion Parameter nd (typical)	≥ 23

#### 3. Additional features

Operating Temperature	- 190°C to + 385°C
Fiber color	Yellow gold

#### 4. Delivery length

>100m

<sup>1</sup>This product under development and classified as a B-sample: For trial of total functional range and the technical requirements, usable for continuous-operating tests, manufacturing of the product is for creation of a specification for the series production and verification of manufacturability. First application tests, dimensions and key parameters according to the series. Not for serial application. Not all customer specifications necessarily fulfilled.

DB-FNT-001-01-0120 Issued January 2020

Supersedes

Created by: C. Schulze

Copyright 2016 © j-fiber GmbH with regard to DIN ISO 16016

Officially registered facility according to EWG No 1221/2009

For further information please contact us:

**j-fiber GmbH**

Tel.: +49-3641-352 100

Fax: +49-3641-352 101

Email: [info@j-fiber.com](mailto:info@j-fiber.com)

